

Colinwell Architectural Masonry

Light Reflectance Value Testing

Colour	YI	x	y
Heather	19.09	0.3648	0.3565
Honey	20.42	0.3881	0.3639
Buff	21.82	0.3632	0.3614
Straw	24.49	0.3731	0.3772
Green	24.72	0.3349	0.3664
Natural	26.09	0.3287	0.3449
Ochre	35.78	0.3727	0.3605
Salmon	36.30	0.3465	0.3496
Oatmeal	38.90	0.3301	0.3455
Sandstone	45.34	0.3531	0.3645
Cream	53.74	0.3648	0.3710
White	61.41	0.3275	0.3428

All Tests carried out to: BS 8493:2008 + A1:2010